
Product Data Sheet

vakuVIP Building Panel



Description:

- Ultra-high-performance insulation through low density and very low thermal conductivity
- Evacuated product core made of compressed microporous silica, opacifiers and fibres
- vakuVIP B2 with a special flame-retardant high-barrier film for use in the construction industry
- 4 mm recycled plastic board on both sides as a mechanical protective layer, with an EPS edge insert around all four sides

Benefits:

- **Protected vacuum insulation panel** for enhanced mechanical protection
- **Excellent thermal insulation** thanks to very low thermal conductivity
- **Space-saving** thanks to its thin design
- **High compressive strength**
- **Environmentally friendly and safe for health:**
    - Environmentally friendly and sustainable product thanks to the 100% recyclability of the core material
    - Contains no glass fibres
- **Customisable:** available in various sizes and shapes to meet individual requirements
- **Durability:** resistant to ageing and moisture, with a service life of up to 50 years

Applications:

- Insulation below and between roof rafters
- Insulation of window and door reveals
- Insulation of external façades
- Insulation of ceilings, particularly basement ceilings
- Insulation of radiator recesses

Dimensions and Tolerances:

Length* / Width* [mm]	***Tolerances***		***Thickness* [mm]*** ***(plus 4 mm building panel on each side)***	***Thickness Tolerance* [mm]***
	Length* [mm]	***Width* [mm]***		
150 - 500	+1 / -4	+1 / -4	10 - 20 21 - 50	+1 / -1 +2 / -2
500-1000	+1 / -5	+1 / -5	10 - 20 21 - 50	+1 / -1 +2 / -2
>1000	+1 / -5	+1 / -5	10 - 20 21 - 50	+1 / -1 +2 / -2

Other dimensions available on request

For dimensions exceeding 1000 x 600 mm, the cores are assembled from several pieces.

Performance Characteristics (applies to the core product vakuVIP B2):

Density	Thickness > 20 mm: 180 to max. 210 kg/m³ in accordance with DIN EN 1602 Thickness ≤ 20 mm: 180 to max. 250 k/m³ in accordance with DIN EN 1602
Weight	approx. 4 kg/m² at a thickness of 20 mm
Compressive strength (compressive stress at 10% deformation)	≥ 125 kPa in accordance with DIN EN 826
Thermal conductivity λ_{10} value	≤ 0.0040 W/(m*K) initial value before ageing for vakuVIP at an internal pressure of < 5 mbar (measured value when tested in accordance with DIN EN 12667) 0.0070 W/(m*k) design value including ageing and edge effects for vakuVIP
Temperature resistance	-50 to +90°C / -58 to +194°F short-term (approx. 30 min) up to +130°C / 266°F
Service life	Up to 50 years, depending on the application, under dry conditions (relative humidity < 60%) and at temperatures of 5°C to 30°C
Packaging	Packed in cartons, on pallets
Safety information	According to the manufacturer, the core is not classified as hazardous under Regulation (EC) No 1272/2008.

[1] Design value (calculation value) of thermal conductivity in accordance with Z-23.11-1851

U-value:

The core product vakuVIP B2 has building authority approval for Germany issued by the German Institute for Building Technology (DIBt Berlin) under number Z-23.11-1851 (dated 11 November 2013).

The calculation value for the thermal conductivity of this product has been set at **0.007 W/(m*K)**.

U-Wert W/(m²K)	VAKUVIP WLG 0,007 * Dicke VIP in mm
0,70	10
0,35	20
0,23	30
0,17	40
0,14	50

Application Restrictions:

The metallised plastic composite film of the vakuVIP elements must not be damaged by drilling, cutting, milling, nailing, screwing, impact against sharp edges, etc. Damage to the film causes the internal pressure of the panels to rise, resulting in loss of the vacuum and the excellent thermal insulation properties. The thermal conductivity in the non-evacuated state is approx. 0.020 W/(m*K).

Please follow our installation and handling instructions supplied with the product.

Contact Information

Manufacturer:

Vaku-Isotherm GmbH

Schönborner Str. 37

09669 Frankenberg

Telephone: +49 (0) 37206 – 5787 - 10

Email: zentrale@vaku-isotherm.de

Website: www.vaku-isotherm.de