Technical data sheet

vakuVIP Protekt-1 & Protekt-2



Description:

- ultra high-performance insulation due to low density and very low thermal conductivity
- vacuumed core material made from pressed microporous silica, opacifiers and fibres
- vakuVIP B2/EU with special flame-retardant high-barrier film for use in the construction sector
- decoupling fleece layer (1.4 mm) on one or both sides as a mechanical protection

Advantages:

- **Covered vacuum insulation panel** for higher mechanical protection
- **Very good thermal insulation** due to very low thermal conductivity
- **Space-saving** due to thin design
- **High compressive strength**
- **Environmentally friendly and safe for health**:
  - Ecological and sustainable product due to 100% recyclability of the core material
  - Contains no toxic or dangerous substances
  - Contains no glass fibers
- **Customizable**: available in various sizes and shapes to meet individual requirements
- **Durability**: resistant to aging and moisture
- **Life cycle of up to 50 years**

Applications:

- Floor insulation
- Insulation of window and door reveals
- Insulation in facade panels with glass or coated aluminium covers

Dimensions and Tolerances:

Length* / Width* [mm]	***Tolerances***		***Thickness* [mm]***	***Tolerance Thickness* [mm]***
	Length* [mm]	***Width* [mm]***	***(plus 3 mm rubber granulate on one or both sides)***	
150 - 500	+1 / -4	+1 / -4	10 - 20 21 - 50	+1 / -1 +2 / -2
500-1000	+1 / -5	+1 / -5	10 - 20 21 - 50	+1 / -1 +2 / -2
>1000	+1 / -5	+1 / -5	10 - 20 21 - 50	+1 / -1 +2 / -2

**other dimensions available on request*

For dimensions over 1000 x 600 mm, the cores are composed of several parts.

All information is provided to the best of our knowledge. Errors and technical changes are reserved. / REV. 4 as of 25.02.2026

Performance Characteristics:

Density	Thickness > 20 mm: 180 to max. 210 kg/m³ according to DIN EN 1602 Thickness ≤ 20 mm: 180 to max. 250 k/m³ according to DIN EN 1602
Weight	approx. 4 kg/m² at 20 mm thickness
Compressive strength **(Compressive stress at 10 % strain)**	≥ 125 kPa according to DIN EN 826
Thermal conductivity λ_{10}-value	≤ 0,0040 W/(m*K) initial value before aging at an internal pressure under 5 mbar (measurement value according to DIN EN 12667)
Temperature resistance	-50 to +90°C / -58 to +194°F short term up to +120°C / 248°F for about 30 min
Service life	under dry conditions (relative humidity < 60%) and temperatures between 5°C – 30°C, up to 50 years depending on the application
Delivery form	packed in cartons on pallets
Safety Instructions	According to the manufacturer, the core is not a hazardous material according to Directive 91/155/EEC. It does not release any dangerous decomposition products and, to the best of current knowledge, poses no health risk to humans.

	VIP thickness [mm]	**U-Wert [W/(m²K)]**
U-Value (for vakuVIP B2/EU)	10	0,70
	20	0,35
	30	0,23
	40	0,17
	50	0,14
	60	0,12

Application restrictions:

The metallized barrier film of the vakuVIP elements must not be damaged by drilling, cutting, milling, nailing, screwing, or impacting sharp edges, etc. Damage to the film leads to an increase in the internal pressure of the panels, resulting in a loss of vacuum and their excellent thermal insulation properties. The thermal conductivity in the ventilated condition is around 0.020 W/(m*K).

Please refer to our processing instructions included with the product upon delivery.

All information is provided to the best of our knowledge. Errors and technical changes are reserved. / REV. 4 as of 25.02.2026

Contact Information

Manufacturer:

Vaku-Isotherm GmbH

Schönborner Str. 37

09669 Frankenberg

Germany

Phone: +49 (0) 37206 – 5787 - 10

E-Mail: zentrale@vaku-isotherm.de

Website: www.vaku-isotherm.de

All information is provided to the best of our knowledge. Errors and technical changes are reserved. / REV. 4 as of 25.02.2026